Technical Specification

Transport and Main Roads Specifications MRTS83 Anti-Graffiti Protection

November 2019



Copyright

© The State of Queensland (Department of Transport and Main Roads) 2019.

Licence



This work is licensed by the State of Queensland (Department of Transport and Main Roads) under a Creative Commons Attribution (CC BY) 4.0 International licence.

CC BY licence summary statement

In essence, you are free to copy, communicate and adapt this work, as long as you attribute the work to the State of Queensland (Department of Transport and Main Roads). To view a copy of this licence, visit: https://creativecommons.org/licenses/by/4.0/

Translating and interpreting assistance



The Queensland Government is committed to providing accessible services to Queenslanders from all cultural and linguistic backgrounds. If you have difficulty understanding this publication and need a translator, please call the Translating and Interpreting Service (TIS National) on 13 14 50 and ask them to telephone the Queensland Department of Transport and Main Roads on 13 74 68.

Disclaimer

While every care has been taken in preparing this publication, the State of Queensland accepts no responsibility for decisions or actions taken as a result of any data, information, statement or advice, expressed or implied, contained within. To the best of our knowledge, the content was correct at the time of publishing.

Feedback

Please send your feedback regarding this document to: tmr.techdocs@tmr.qld.gov.au

Contents

| 1 | Introduction | 1 |
|-----|---|---|
| 2 | Definition of terms | |
| 3 | Referenced documents | 1 |
| 4 | Quality system requirements | 1 |
| 4.1 | Hold Points, Witness Points and Milestones | |
| 5 | Materials | 2 |
| 5.1 | General | 2 |
| 5.2 | Registered suppliers and proprietary products | 2 |
| 5.3 | Non-sacrificial (permanent) coating | 2 |
| 5.4 | Sacrificial (non-permanent) coating | |
| 6 | Application | 2 |
| 6.1 | General | 2 |
| 6.2 | Areas to be coated | 2 |
| 6.3 | Surface preparation | 2 |
| 6.4 | Application of coating | 3 |
| 7 | Supplementary requirements | 3 |

1 Introduction

This Technical Specification applies to the supply and application of anti-graffiti protection to roadwork and bridgework structures.

This Technical Specification shall be read in conjunction with MRTS01 *Introduction to Technical Specifications*, MRTS50 *Specific Quality System Requirements* and other Technical Specifications, as appropriate.

This Technical Specification forms part of the Transport and Main Roads Specifications Manual.

2 Definition of terms

The terms used in this Technical Specification shall be as defined in Clause 2 of MRTS01 *Introduction to Technical Specifications*.

In addition, terms listed in Table 2 are applicable to this Technical Specification.

Table 2 - Definition of terms

| Term | Definition |
|--|--|
| Anti-graffiti protection coating | A coating that prevents graffiti paint bonding to substrates |
| Non-sacrificial anti-graffiti protection coating | Permanent protection against graffiti paint |
| Sacrificial anti-graffiti protection coating | Non-permanent (temporary) protection against graffiti paint |

3 Referenced documents

Table 3 lists documents referenced in this Technical Specification.

Table 3 – Referenced documents

| Reference | Title |
|-----------|--|
| MRTS01 | Introduction to Technical Specifications |
| MRTS50 | Specific Quality System Requirements |
| 1441 | Australian Paint Approval Scheme Specification, Permanent Graffiti Barrier |
| 1442 | Australian Paint Approval Scheme Specification, Temporary Graffiti Barrier |

4 Quality system requirements

4.1 Hold Points, Witness Points and Milestones

General requirements for Hold Points, Witness Points and Milestones are specified in Clause 5.2 of MRTS01 *Introduction to Technical Specifications*.

The Hold Points, Witness Points and Milestones applicable to this Technical Specification are summarised in Table 4.1.

Table 4.1 - Hold Points, Witness Points and Milestones

| Clause | Hold Point | Witness Point | Milestone |
|--------|------------|------------------------|-----------|
| 6.4 | | Application of coating | |

5 Materials

5.1 General

All anti-graffiti protection coatings shall be clear in colour.

5.2 Registered suppliers and proprietary products

Work Operations that require the use of registered suppliers and proprietary products are listed in Table 5.2.

Table 5.2 - Items requiring use of registered suppliers and proprietary products

| Clause | Category of Work |
|-----------|---|
| 5.3 and 6 | Application of non-sacrificial (permanent) anti-graffiti protection coating |
| 5.4 and 6 | Application of sacrificial (non-permanent) anti-graffiti protection coating |

Clauses 1 and 2 of Annexure MRTS83.1 list the registered proprietary products to be used for the project.

Registered suppliers and proprietary products are listed in Transport and Mains Roads *Product Index for Bridges and Other Structures*. Access this document via https://www.tmr.qld.gov.au/business-industry/Business-with-us/Approved-products-and-suppliers/Bridges-and-other-structures-approved-products-and-suppliers.

5.3 Non-sacrificial (permanent) coating

Non-sacrificial (permanent) anti-graffiti protection coating shall be a clear single or two-part exterior anti-graffiti coating approved under the *Australian Paint Approval Scheme, Specification No. 1441*.

Clause 1 of Annexure MRTS83.1 lists the registered products to be used for the project.

5.4 Sacrificial (non-permanent) coating

Sacrificial (non-permanent) anti-graffiti protection coating shall be a clear exterior coating approved under the *Australian Paint Approval Scheme, Specification No. 1442*.

Clause 2 of Annexure MRTS83.1 lists the registered products to be used for the project.

6 Application

6.1 General

Anti-graffiti protection coating shall be a registered product in accordance with Clause 5 and applied in accordance with the manufacturer's specifications / recommendations.

Products which exhibit yellowing with age shall not be used.

6.2 Areas to be coated

The areas to be treated with anti-graffiti protection coating under the Contract are stated in Clause 3 of Annexure MRTS83.1.

6.3 Surface preparation

Concrete surfaces to which anti-graffiti protection coating is to be applied shall first be cleaned of all foreign matter and markings.

6.4 Application of coating

On new concrete, the Contractor shall be responsible for maintaining a clean surface or restoring the surface to an as-constructed condition prior to application of the coating. It is recommended that the anti-graffiti treatment be applied soon after the concrete surface has been constructed.

Following surface preparation, the anti-graffiti protection coating shall be applied by experienced applicators in accordance with the manufacturer's specifications / recommendations. The minimum application rate shall be 100 mL/m² for off-form concrete. Heavy run down or streaking shall not occur.

Application of anti-graffiti coating shall be a Witness Point. Witness Point 1

7 Supplementary requirements

The requirements of this Technical Specification shall vary in accordance with the supplementary requirements provided in Clause 4 of Annexure MRTS83.1.