

Technical Specification

Transport and Main Roads Specifications  
MRTS36 Recycled Glass Aggregate

November 2025

(ATS 3050 Supply of Recycled Crushed Glass Sand, Ed 2.0 December 2023)



## Copyright

© The State of Queensland (Department of Transport and Main Roads) 2025.

## Licence



This work is licensed by the State of Queensland (Department of Transport and Main Roads) under a Creative Commons Attribution (CC BY) 4.0 International licence.

## CC BY licence summary statement

In essence, you are free to copy, communicate and adapt this work, as long as you attribute the work to the State of Queensland (Department of Transport and Main Roads). To view a copy of this licence, visit: <https://creativecommons.org/licenses/by/4.0/>

## Translating and interpreting assistance



The Queensland Government is committed to providing accessible services to Queenslanders from all cultural and linguistic backgrounds. If you have difficulty understanding this publication and need a translator, please call the Translating and Interpreting Service (TIS National) on 13 14 50 and ask them to telephone the Queensland Department of Transport and Main Roads on 13 74 68.

## Disclaimer

While every care has been taken in preparing this publication, the State of Queensland accepts no responsibility for decisions or actions taken as a result of any data, information, statement or advice, expressed or implied, contained within. To the best of our knowledge, the content was correct at the time of publishing.

## Feedback

Please send your feedback regarding this document to: [tmr.techdocs@tmr.qld.gov.au](mailto:tmr.techdocs@tmr.qld.gov.au)

## Purpose

This ancillary document outlines the adopted national Austroads Technical Specification ATS 3050 *Supply of Recycled Crushed Glass Sand* and modified Queensland-specific content with tracked changes.

The following table summarises the relationship between the Austroads Technical Specification ATS 3050 *Supply of Recycled Crushed Glass Sand* and this document:

| <b>Type of Content</b>       | <b>Display</b>                          |
|------------------------------|---|
| National content adopted     | National content adopted                |
| National content not adopted | <del>National content not adopted</del> |
| Queensland-specific content  | <u>Queensland-specific content</u>      |

## **About this document**

The document adopts and modifies Austroads Technical Specification ATS 3050 *Supply of Recycled Crushed Glass Sand* as part of national harmonisation. It sets out the requirements for the manufacture and supply of Recycled Crushed Glass (RCG).

## **How to use this document**

This document includes the national guidance and Queensland-specific advice while following the structure established in Austroads Technical Specifications.

Queensland-specific advice includes practices which vary from national practice because of local environmental conditions (such as geography, soil types, climate); different funding practices; local research; local legislation requirements; and to expand instruction on particular issues.

This document:

- [sets out how the Austroads Technical Specification ATS 3050 \*Supply of Recycled Crushed Glass Sand\* applies in Queensland](#)
- [has precedence over the Austroads Technical Specification ATS 3050 \*Supply of Recycled Crushed Glass Sand\* when applied in Queensland](#)
- [has the same clause numbering and headings as the Austroads Technical Specification ATS 3050 \*Supply of Recycled Crushed Glass Sand\*.](#)

Transport and Mains Roads provides an ancillary document which outlines adopted national and modified Queensland-specific content with tracked changes. To access a copy click on the below link: [Ancillary documents for harmonised Technical Specifications.](#)

## **Terminology**

The following general amended definitions apply when reading this document.

| <b><u>Reference to...</u></b>        | <b><u>Means</u></b>   |
|--------------------------------------|---|
| <a href="#"><u>Shall</u></a>         | <a href="#"><u>Denotes mandatory requirements.</u></a>  |
| <a href="#"><u>Must</u></a>          | <a href="#"><u>Denotes mandatory requirements.</u></a>  |
| <a href="#"><u>Principal</u></a>     | <a href="#"><u>The State of Queensland acting through the Department of Transport and Main Roads.</u></a>     |
| <a href="#"><u>Administrator</u></a> | <a href="#"><u>The Administrator will be responsible for the overall administration of this Contract.</u></a> |

# Contents

|   |           |
|---|-----------|
| <b>Purpose .....</b>  | <b>i</b>  |
| <b>About this document .....</b>  | <b>ii</b> |
| <b>How to use this document .....</b>   | <b>ii</b> |
| <b>Terminology.....</b>   | <b>ii</b> |
| <b>1 Scope .....</b>  | <b>1</b>  |
| <b>2 Referenced documents.....</b>  | <b>2</b>  |
| <b>3 Definitions .....</b>  | <b>4</b>  |
| <b>4 Quality system requirements .....</b>  | <b>5</b>  |
| <b>5 Glass source .....</b>   | <b>6</b>  |
| <b>6 Chemical and other material requirements.....</b>                                  | <b>7</b>  |
| <b>7 Properties for use as a granular material .....</b>                                | <b>8</b>  |
| <b>8 Properties of RCG used in concrete .....</b>                                       | <b>9</b>  |
| General .....   | 9         |
| Alkali-Silica reactivity.....   | 12        |
| <b>9 Testing and conformance.....</b>   | <b>12</b> |
| <b>Appendix A: Summary of Hold Points, Witness Points, Milestones and Records .....</b> | <b>15</b> |

## 1 Scope

- 1.1 ~~This Austroads~~ Technical Specification ~~ATS 3050~~ sets out the requirements for the manufacture and supply of recycled crushed glass (RCG) as a sand aggregate replacement in the following applications:
- a) As a granular material, including:
    - i. bedding and haunching of pipes and conduits
    - ii. side fill and backfill of pipes and conduits
    - ~~iii. bedding and joint filling in block paving~~
    - ~~iv.iii.~~ drainage medium applications
    - ~~v.iv.~~ embankment fill and earthworks applications
    - ~~vi.v.~~ landscaping applications, and
    - ~~vii.vi.~~ partial aggregate replacement (mechanical stabilisation) for granular base and subbase material (Subtype 2.3, 2.4 and 2.5).
  - b) As a partial 'fine' aggregate replacement in some asphalt applications.
  - c) As a partial fine aggregate replacement in:
    - i. Normal Class Concrete used in general works.

~~d) Special Class Concrete used in road pavements. As a partial fine aggregate replacement in concrete used in:~~

    - i. Lean Mix Concrete Sub-base for Pavements.
    - ii. Concrete Pavement Base.
- ~~1.2 RCG used in Special Class Concrete for bridgeworks and other structures, such as retaining walls, is excluded from the scope of this Specification.~~
- ~~1.3.1.2~~ All RCG must comply with Clause 6. Where RCG is used as a granular material or used in concrete, it must also comply with the properties specified in Clause 7 or Clause 8 respectively.
- 1.3 This Technical Specification shall be read in conjunction with MRTS01 Introduction to Technical Specifications, MRTS50 Specific Quality System Requirements and other Technical Specifications as appropriate.

[1.4 This Technical Specification forms part of the Transport and Main Roads Specifications Manual.](#)

## 2 Referenced documents

2.1 [The following documents are referenced in this Specification. The requirements of the referenced documents listed in Table 2.1 below apply to this Technical Specification. Where there are inconsistencies between this Technical Specification and the referenced documents, the requirements in this Technical Specification shall take precedence.](#)

**[Table 2.1 – Reference documents](#)**

| <a href="#">Reference</a>                 | <a href="#">Title</a>  |
|---|--|
| <b>Australian / New Zealand Standards</b> |  |
| AS 1012.20.1                              | <i>Methods of testing concrete: determination of chloride and sulphate in hardened concrete and aggregates (nitric acid extraction method)</i> |
| AS 1141.3.1                               | <i>Methods for sampling and testing aggregates: aggregates</i>   |
| AS 1141.4                                 | <i>Methods for sampling and testing aggregates: bulk density of aggregate</i>  |
| AS 1141.5                                 | <i>Methods for sampling and testing aggregates: particle density and water absorption of fine aggregate</i>                                    |
| AS 1141.11.1                              | <i>Methods for sampling and testing aggregates: particle size distribution (sieving method)</i>  |
| AS 1141.12                                | <i>Methods for sampling and testing aggregates: material finer than 75 µm in aggregates (by washing)</i>                                       |
| AS 1141.24                                | <i>Methods for sampling and testing aggregates: aggregate soundness: evaluation by exposure to sodium sulfate solution</i>                     |
| AS 1141.34                                | <i>Methods for sampling and testing aggregates: organic impurities other than sugar</i>  |
| AS 1141.35                                | <i>Methods for sampling and testing aggregates: detection of sugar contamination in concrete aggregates</i>                                    |
| AS 1141.60.1                              | <i>Methods for sampling and testing aggregates potential alkali-silica reactivity: accelerated mortar bar method</i>                           |
| AS 1141.60.2                              | <i>Methods for sampling and testing aggregates potential alkali-silica reactivity: concrete prism method</i>                                   |
| AS 1141.66                                | <i>Methods for sampling and testing aggregates: methylene blue adsorption value of fine aggregate and mineral fillers</i>                      |

| <b>Reference</b>  | <b>Title</b>   |
|---|--|
| AS 1289.4.1.1   | <i>Methods of testing soils for engineering purposes: soil chemical tests – determination of the organic matter content of a soil: normal method</i>                                 |
| AS 1379   | <i>Specification and supply of concrete</i>  |
| AS 2758.1   | <i>Aggregates and rock for engineering purposes: concrete aggregates</i>   |
| AS/NZS ISO 9001   | <i>Quality management systems: requirements</i>  |
| SA HB 79  | <i>Alkali aggregate reaction: guidelines on minimising the risk of damage to concrete structures in Australia</i>  |
| <b>Austrroads</b>   |  |
| AP-C87-15   | <i>Austrroads glossary of terms</i>  |
| <b>NSW Environmental Protection Authority</b>                       |  |
| <a href="#">EPA RRO</a>   | <a href="#"><i>Resource Recovery Order under Part 9, Clause 93 of the Protection of the Environment Operations (Waste) Regulation 2014 – The recovered glass sand order 2014</i></a> |
| <b>ASTM International</b>   |  |
| ASTM C295   | <i>Standard guide for petrographic examination of aggregates for concretes</i>   |
| <b>Queensland Department of Environment, Science and Innovation</b> |  |
| <a href="#">EOWC</a>  | <a href="#"><i>End of Waste Code – Glass Fines (EOWC010001051)</i></a>   |
| <b>Transport and Main Roads Technical Documents</b>                 |  |
| <a href="#">MRTS01</a>  | <a href="#"><i>Introduction to Technical Specifications</i></a>  |
| <a href="#">MRTS04</a>  | <a href="#"><i>General Earthworks</i></a>  |
| <a href="#">MRTS05</a>  | <a href="#"><i>Unbound Pavements</i></a>   |
| <a href="#">MRTS30</a>  | <a href="#"><i>Asphalt Pavements</i></a>   |
| <a href="#">MRTS39</a>  | <a href="#"><i>Lean-mix Concrete Subbase</i></a>   |
| <a href="#">MRTS40</a>  | <a href="#"><i>Concrete Pavement Base</i></a>  |
| <a href="#">MRTS41</a>  | <a href="#"><i>Concrete Pavement Base (Ancillary Works)</i></a>  |
| <a href="#">MRTS50</a>  | <a href="#"><i>Specific Quality Systems – Requirements</i></a>   |
| <a href="#">MRTS70</a>  | <a href="#"><i>Concrete</i></a>  |
| <a href="#">MRTS101</a>   | <a href="#"><i>Aggregates for Asphalt</i></a>  |
| <a href="#">QRS1-QRS5</a>   | <a href="#"><i>Quarry Registration System documents (QRS1-QRS5)</i></a>  |

### 3 Definitions

3.1 ~~In addition to the definitions in AP-C87-15 and AS 1379, the following definitions apply to this Specification. The terms used in this Technical Specification shall be defined in Clause 2 of MRTS01 *Introduction to Technical Specifications*. Additionally, terminology relevant to this Technical Specification is defined in Table 3.1 below.~~

***Table 3.1 - Definitions of terms***

| <b>Term</b>              | <b>Definition</b>   |
|--------------------------|---|
| Backfill material        | Material placed in confined excavations for culverts, structures, conduits, pits <del>and so on</del> , or in some instances, to fill excavations of unsuitable material. Backfill includes bedding material and materials placed in the foundation bedding, haunch, side and overlay zones during culvert backfill.              |
| Bedding material         | Material suitable for use in the foundation bedding zone of culverts, pipes, conduits, pits, and similar structures, and in the haunching of pipes and conduits.  |
| Concrete applications    | Includes low-risk applications such as footings and plinths (sign support for general works structures, lighting columns, traffic signals, etc.), kerbs and channel, paving for bicycle paths/shared paths, footpaths, medians, driveways, and aesthetic structures such as park benches, small planter boxes and garden reliefs. |
| Concrete pavement        | A pavement structure made from concrete materials which may contain reinforcement. This is inclusive of the concrete base layer and lean mix concrete subbase.  |
| Drainage medium          | A free draining backfill material used in subsoil drainage applications material including, but not limited to subsoil drains, sheet filter drains and vertical/wick drains.  |
| Embankment core zone     | The central zone of an embankment adjacent to the embankment (outer zone) and overlying embankment (upper zone) and pavement structure.   |
| Embankment fill material | Material placed in an embankment to subgrade level, and used to backfill subgrade treatments or to replace unsuitable material. Includes both earth fill and rock fill.   |
| Fine aggregates          | <del>A general term for aggregate that substantially passes the 4.75 mm sieve. Mostly composed of sand. Aggregate having a nominal size of less than 5 mm.</del>  |
| Haunch material          | The material immediately above the foundation bedding zone for the installation of pipe culverts.   |

| <b>Term</b>              | <b>Definition</b>   |
|--------------------------|---|
| Legislative Requirements | <del>The regulations, policies and codes of practice issued pursuant to any legislation for the protection or management of the environment which are applicable to the manufacture of RCG.</del> |
| Recycled glass           | <u>Glass sourced from the collection of domestic or commercial waste. This includes glass collected from domestic commingled recycling collections.</u>   |
| Side fill                | The material placed adjacent to the centre of pipe culverts.  |
| Total fine aggregates    | The sum of the fine aggregates from all sources within the concrete fine aggregate mix.   |

## 4 Quality system requirements

- 4.1 RCG must be manufactured under a Quality Management System which conforms to AS/NZS ISO 9001.
- 4.2 The manufacturer of the RCG must have a current license or exemption for the recovery of resources from waste issued by the relevant state or territory environmental authority.
- 4.3 The Contractor must prepare and implement a Quality Plan that includes the documentation in Table 4.3. However, if the Quality Plan has previously been provided to the Principal Administrator or the manufacturer has been approved / registered by the Principal Administrator, it is not necessary to resubmit the Quality Plan, unless there has been a change to the manufacturing process or the source of the unprocessed materials.

**Table 4.3 – Quality plan**

| <b>Clause</b> | <b>Description of document</b>  |
|---------------|---|
| 5.1           | Details of the source of glass and manufacturing process  |
| <u>6</u>      | <u>Complies with MRTS50 Specific Quality System Requirements</u>  |
| 6.1           | Applicable Legislative Requirements <u>including but not limited to the End of Waste Code (EOWC010001051) Queensland 2022</u> |
| 8.1           | Target material properties  |
| 9             | Procedures for stockpile management, management of Lots and testing   |

4.4 Glass processing sites for asphalt and concrete fine aggregates (excluding fine aggregates for Normal Class concrete) shall be registered under Transport and Main Roads Quarry Registration System (QRS).

4.5 The use of recycled glass shall not commence until all relevant production procedures have been accepted by the Administrator. **Hold Point 1 Record**

| HOLD POINT 1       |   |
|--------------------|---|
| Process Held       | Quality system conformance.   |
| Submission Details | Where applicable, the documentation listed in Clause 4 must be submitted to the <u>Principal Administrator</u> at least <u>107</u> working days prior to the commencement of the supply of the RCG to the Site. |

## 5 Glass source

5.1 The Quality Plan must include details of:

- a) the source(s) of glass
- b) the production plant and processes, ~~and~~
- c) methods to ensure that the level of contamination complies with this Technical Specification, and
- ~~c~~d) compliance with EOWC Glass Fines requirements and procedures for stockpile management and traceability as part of the lot control and as applicable, sub lot control.

5.2 RCG must be produced from food and beverage container glass, or window glass. The source material must be essentially free of glass from the following sources:

- a) cathode ray tubes
- b) fluorescent and incandescent lights
- c) glass recovered from electrical equipment
- d) glass recovered from a laboratory source
- e) porcelain products or cook tops, ~~and~~
- f) glass from hazardous waste containers, and
- ~~f~~g) paper, cork, metals (including heavy metals), brick, plaster, plastic, rubber, wood, clay, paint, and other deleterious materials.

5.3 RCG must be free from any putrid odour.

## 6 Chemical and other material requirements

6.1 The Quality Plan must include:

- a) details of the applicable Legislative Requirements [including End of Waste Code Glass Fines \(EOWC010001051\)](#), and
- b) procedures for ensuring that the manufacture of RCG is carried out in accordance with the Legislative Requirements.

6.2 The Contractor must ensure that the chemical concentrations and other characteristics of the RCG comply with any applicable requirements specified in the Legislative Requirements.

6.3 ~~If maximum permissible levels of contaminants are not specified in the applicable Legislative Requirements, the maximum levels in Table 1 of the EPA RRO apply and the sampling and testing for contaminants must comply with Clauses 4.1 to 4.8 (inclusive) of the EPA RRO. Maximum concentration limits for chemicals and other attributes shall be as per Table 6.3.~~

6.4 ~~For Attributes 12 -14 in Table 1 of the EPA RRO, the Principal may approve an alternative test method. Details of any proposed alternative test method must be included in the Quality Plan. This Clause 6.4 does not apply in New South Wales.~~

**Table 6.3 - Maximum concentration limits for chemicals and other attributes**

| <u>Quality characteristics</u>          | <u>Absolute maximum concentration (mg/kg 'dry weight' unless otherwise specified)</u> |
|---|---|
| <a href="#">Arsenic</a>                 | <a href="#">20</a>  |
| <a href="#">Cadmium</a>                 | <a href="#">1.5</a>   |
| <a href="#">Chromium (total)</a>        | <a href="#">40</a>  |
| <a href="#">Copper</a>                  | <a href="#">120</a>   |
| <a href="#">Lead</a>                    | <a href="#">100</a>   |
| <a href="#">Mercury</a>                 | <a href="#">1</a>   |
| <a href="#">Molybdenum</a>              | <a href="#">10</a>  |
| <a href="#">Nickel</a>                  | <a href="#">20</a>  |
| <a href="#">Zinc</a>                    | <a href="#">300</a>   |
| <a href="#">Electrical Conductivity</a> | <a href="#">2 dS/m or 2000 µS/cm</a>  |
| <a href="#">Total Organic Carbon</a>    | <a href="#">2.00%</a>   |

## 7 Properties for use as a granular material

- 7.1 This Clause 7 only applies where RCG is used as a granular material.
- 7.2 RCG particles must be cubic in shape and free from sharp edges and elongated particles [verified through visual inspections](#).
- 7.3 The particle size distribution for RCG must be determined in accordance with AS 1141.11.1.
- 7.4 ~~The applicable grading classification type must be determined from~~ Table 7.4 ~~provides application offer the nominated~~ RCG ~~application and relevant departmental~~ [Technical Specifications](#).

**Table 7.4 – Grading Classification Type**

| Application <sup>(4)</sup>   | Grading Classification Type <a href="#">Technical Specification</a> |
|--|---|
| Bedding and haunch of drainage pipes, conduits, and services                           | <del>Type A</del> <a href="#">MRTS04</a>                            |
| Side zone and backfill of drainage trenches  | <del>Type A</del> <a href="#">MRTS04</a>                            |
| Bedding for segmental or block paving  | <del>Type B</del> <a href="#">MRTS03</a>                            |
| Joint filling<br>(i.e. filling the voids between individual segmental or block pavers) | <del>Type C</del> <a href="#">MRTS04</a>                            |
| Drainage medium  | <del>Type D</del> <a href="#">MRTS04</a>                            |
| Embankment (core zone) fill <sup>(21)</sup>  | <del>Type E</del> <a href="#">MRTS04</a>                            |
| Landscaping  | <del>Type F</del> <a href="#">MRTS04</a><br><a href="#">MRTS16</a>  |
| Partial aggregate replacement in asphalt   | <del>Type G</del> <a href="#">MRTS101</a>                           |
| <a href="#">Pavements – Unbound Granular</a>   | <a href="#">MRTS05</a>  |

Notes:

~~<sup>(4)</sup> These grading classifications do not apply to RCG for partial aggregate replacement for use in granular materials.~~

<sup>(21)</sup> RCG must be used [as Class A2 material](#) in the core zone of embankments, [provided it meets the coefficient of uniformity requirements specified in MRTS04 General Earthworks](#). RCG must not be placed within upper or outer zones of the embankment.

~~7.5 The particle size distribution must comply with Table 7.5 for the applicable grading classification type. The minimum frequency of testing is one test per Lot. If the RCG is a component of a blend with other materials, other grading limits may apply.~~

~~Table 7.5 – Particle Size Distribution<sup>(1)</sup>~~

| AS Sieve (mm) | Percentage Passing by Mass for Each Grading Classification |        |        |        |        |        |        |
|---------------|--|--------|--------|--------|--------|--------|--------|
|               | Type-A   | Type-B | Type-C | Type-D | Type-E | Type-F | Type-G |
| 9.50          | 100  | 100    | =      | =      | 100    | 100    |        |
| 6.7           | -  | -      | -      | -      | -      | -      | 100    |
| 4.75          | 85-100   | 95-100 | -      | 100    | 70-100 | 85-100 | 98-100 |
| 2.36          | 50-100   | 80-100 | 100    | =      | =      | =      | =      |
| 1.18          | -  | 50-85  | 90-100 | 0-2    | -      | -      | -      |
| 0.60          | 20-90  | 25-60  | 60-90  | -      | -      | -      | -      |
| 0.30          | 10-60  | 10-30  | 30-60  | -      | -      | -      | -      |
| 0.15          | 0-25   | 5-15   | 15-30  | -      | -      | -      | -      |
| 0.075         | 0-10   | 0-10   | 5-10   | -      | -      | -      | -      |

Note:

<sup>(1)</sup> ~~Unless specified otherwise, the grading limits specified in Table 7.5 (except for Type G) do not apply when the RCG is a component of a blend.~~

## 8 Properties of RCG used in concrete

### General

8.1 This Clause 8 only applies where RCG is used in the manufacture of concrete.

8.2 RCG used as a [partial replacement of](#) fine aggregate in the manufacture of concrete must:

- a) comply with AS 2758.1
- b) comprise of particles which are predominantly cubic in shape, free from sharp edges and elongated particles [verified through visual inspections](#), and
- c) have a maximum nominal size of 5 mm.

~~8.3 The proportion of RCG must not exceed 15% of the fine aggregate (measured by mass) in the concrete.~~

~~8.4 The Contractor may submit a proposal to the Principal to accept the following for Normal Class Concrete:~~

- ~~a) RCG comprising up to 20% of the fine aggregate, or~~
- ~~b) Unwashed RCG comprising up to 10% of the fine aggregate.~~

~~The Principal is under no obligation to accept any such proposal.~~

~~8.58.3~~ The RCG must be tested for compliance with ~~Table 8.53(a) and Table 8.3(b)~~.

***Table 8.3(a) – Requirements for Recycled Crushed Glass Used in Concrete – Source testing***

| <u>Property</u>                                | <u>Standards and test methods</u> | <u>Minimum test frequency</u> | <u>Requirements</u>                    |
|--|-----------------------------------|-------------------------------|--|
| <u>Durability</u>                              | <u>AS 2758.1, Clause 9.2.2.3</u>  | <u>1 test per Lot</u>         | <u>AS 2758.1, Clause 9.2.2.3</u>       |
| <u>Water absorption</u>                        | <u>AS 1141.5</u>                  | <u>1 test per Lot</u>         | <u>≤ 1.0%</u>                          |
| <u>Weighted percent loss (sodium sulphate)</u> | <u>AS 1141.24</u>                 | <u>1 test per Lot</u>         | <u>6.0% max weighted average loss</u>  |
| <u>Particle density</u>                        | <u>AS 1141.5</u>                  | <u>1 test per Lot</u>         | <u>≥ 2.1, &lt; 3.2 t/m<sup>3</sup></u> |

***Table 8.53(b) – Requirements for Recycled Crushed Glass Used in Concrete – Product testing***

| <u>Property</u>               | <u>Standards and test methods</u> | <u>Minimum test frequency</u>        | <u>Requirements</u>  |
|-------------------------------|-----------------------------------|--------------------------------------|--|
| <u>Sampling of aggregates</u> | <u>AS 1141.3.1</u>                | <u>1 test per Lot <sup>(1)</sup></u> |  |
| Particle size distribution    | AS 1141.11.1 and AS 1141.12       | 2 tests per Lot <sup>(1)</sup>       | The limits of deviation for manufactured fine aggregate in Table 2 of AS 2758.1                                |
| Sugar in aggregate            | AS 1141.35                        | 1 test per Lot                       | Less than one part in 10 000   |
| <u>Sulphates content</u>      | AS 1379<br>AS 1012.20.1           | 1 test per Lot                       | Report if exceeds 0.01%  |
| Chloride content              | AS 1379<br>AS 1012.20.1           | 1 test per Lot                       | Report if exceeds 0.01%<br>Max 0.04% for embedded steel reinforcement concrete<br>Max 0.15% for plain concrete |

| Property  | Standards and test methods               | Minimum test frequency    | Requirements   |
|---|--|---------------------------|--|
| Organic impurities (vegetable matter and wood particles)      | AS 1141.34<br>AS 1289.4.1.1              | 1 test per Lot            | Test fails if colour is darker than reference colour (AS 1141.34) max 0.5% (AS 1289.4.1.1) |
| <del>Durability</del>   | <del>AS 2758.1,<br/>Clause 9.2.2.3</del> | <del>1 test per Lot</del> | <del>AS 2758.1, Clause 9.2.2.3</del>   |
| Methylene Blue Absorption Value (MBV) <sup>(2)</sup>          | AS 1141.66                               | 1 test per Lot            | ≤ 5.0%   |
| Deleterious fines index (DFI) <sup>(3)</sup>                  | AS 2758.1                                | 1 test per Lot            | ≤ 150  |
| Bulk density (compacted)                                      | AS 1141.4                                | 1 test per Lot            | 1 200 kg/m <sup>3</sup> minimum  |
| <del>Water absorption</del>                                   | <del>AS 1141.5</del>                     | <del>1 test per Lot</del> | <del>≤ 1.0%</del>  |
| <del>Soundness (sodium sulphate)</del>                        | <del>AS 1141.24</del>                    | <del>1 test per Lot</del> | <del>6.0% max weighted average loss</del>  |
| <del>Percent Abrasion (Micro-Deval) Loss <sup>(4)</sup></del> | <del>ASTM D7428<br/>Q229A</del>          | <del>1 test per Lot</del> | <del>≤ 15%</del>   |

Notes:

(1) If the lot size is between 500 and 1000 tonnes, the minimum test frequency is 3 tests per Lot.

(2) Required if material finer than 2 µm is more than 1.0% of grading.

(3) DFI is the product of the MBV and the passing 75 µm value.

(4) [When intended for use in concrete wearing surface directly trafficked by vehicles not including footpaths or cycleways.](#)

~~8.68.4~~ The particle size distribution for RCG must be determined in accordance with AS 1141.11.1 and AS 1141.12. The particle size distribution must not deviate from the submitted grading (as defined by AS 2758.1) by more than the limits of deviation for manufactured fine aggregate in AS 2758.1, as summarised in [Table 8.64](#).

**Table 8.64 – RCG Limits of Derivation**

| Sieve Aperture (mm) | Limits of Deviation<br>Sieve Aperture (%) |
|---------------------|---|
| 4.75                | ± 5                                       |
| 2.36                | ± 10                                      |
| 1.18                | ± 15                                      |
| 0.60                | ± 15                                      |
| 0.30                | ± 10                                      |
| 0.15                | ± 5                                       |
| 0.075               | ± 5                                       |

**8.78.5** Apparent particle density, dry particle density, saturated surface dry density and water absorption must be determined in accordance with AS 1141.5.

**8.88.6** Aggregates must be assessed for any unstable silica minerals by petrographic examination in accordance with ASTM C295.

### **Alkali-Silica reactivity**

**8.98.7** Unless the [Principal Administrator](#) has approved the concrete mix and waived the requirement for Alkali-Silica Reactivity (ASR) testing, RCG as fine aggregate replacement must be tested in accordance with AS 1141.60.1. ~~However, if AS 1141.60.1 is not suitable for the type of aggregate being tested, or its suitability is unknown, testing in accordance with AS 1141.60.2 must be undertaken.~~

**8.108.8** If the RCG is identified as having a potential for ASR when tested in accordance with AS 1141.60.1 ~~or AS 1141.60.2~~, then treatment to control the effect must be in accordance with SA HB 79 [and the applicable Technical Specification for the concrete \(MRTS39 Lean-mix Concrete Subbase, MRTS40 Concrete Pavement Base or MRTS70 Concrete\)](#).

## **9 Testing and conformance**

9.1 Sampling must be carried out in accordance with AS 1141.3.1.

**Table 9.1 – Standard Test Methods**

| <b>Property to be Tested</b>                   | <b>Method No.</b>  |
|--|--|
| <a href="#">Sampling of aggregates</a>         | <a href="#">AS 1141.3.1</a>  |
| <a href="#">Particle size distribution</a>     | <a href="#">AS 1141.11.1</a>   |
| <a href="#">Material finer than 75 µm</a>      | <a href="#">AS 1141.12</a>   |
| <a href="#">Chemicals – sample preparation</a> | <a href="#">USEPA SW 846 Method 3051A Microwave assisted acid digestion of sediments, sludges, soils, and oils</a>   |
| <a href="#">Chemicals – analysis</a>           | <a href="#">USEPA SW 846 Method 6010C Inductively coupled plasma - atomic emission spectrometry, or an equivalent analytical method with a detection limit &lt; 10% of the stated absolute maximum concentration in Table 6.3.</a>   |
| <a href="#">Mercury concentration</a>          | <a href="#">USEPA SW 846 Method 7471B Mercury in solid or semisolid waste (manual cold vapour technique), or an equivalent analytical method with a detection limit &lt; 20% of the stated absolute maximum concentration in Table 6.3.</a>  |
| <a href="#">Total organic carbon content</a>   | <a href="#">Method 105 (Organic Carbon) and using a 2 gram sample in Schedule B (3): <i>Guideline on Laboratory Analysis of Potentially Contaminated Soils</i>, National Environment Protection (other published or validated classical chemistry technique or instrumentation technique) <sup>(1)</sup></a>                                 |
| <a href="#">Electrical conductivity</a>        | <a href="#">Method 104 (Electrical Conductivity) in Schedule B (3): <i>Guideline on Laboratory Analysis of Potentially Contaminated Soils</i>, National Environment Protection (Assessment of Site Contamination) Measure 1999 or APHA 2510 B. (other published or validated classical chemistry technique or instrumentation technique)</a> |

**Note:**

<sup>(1)</sup> [Where an equivalent analytical method is used, the detection limit must be equal to or less than that nominated for the methods in Table 9.1. Instrumentation techniques may include Ion Chromatography / Inductively Coupled Plasma / Discrete Analyser and so on. Nata endorsed test results are evidence of a validated technique.](#)

9.2 The maximum Lot size is 500 tonnes, unless otherwise relaxed under Clause 9.3. Nonconforming Lots must not be incorporated into the Works.

9.3 The Contractor may submit a proposal to the [Principal Administrator](#) to increase the size of a Lot where the process control has achieved a consistent product, as demonstrated by 5 consecutive Lots conforming to the requirements of this [Technical Specification](#). The maximum Lot size may be increased as specified in Table 9.3. The [Principal Administrator](#) is under no obligation to accept any such proposal.

**Table 9.3 – Revision to Maximum Lot Size**

| Number of Consecutive Complying Lots | Maximum Lot Size |
|--------------------------------------|------------------|
| < 5                                  | 500 tonnes       |
| ≥ 5                                  | 1000 tonnes      |

9.4 ~~Unless the requirement to provide test certificates is waived by the Principal, t~~The Contractor must submit test certificates to demonstrate compliance with the requirements of this [Technical Specification](#) prior to Incorporation of the RCG into the Works. The test certificates must include details about the source of the RCG, test results and any other relevant information. **Hold Point 2 Record**

| HOLD POINT 2       |   |
|--------------------|---|
| Process Held       | Incorporation of RCG into the Works.  |
| Submission Details | The test results must be submitted to the <a href="#">Principal Administrator</a> prior to the incorporation of the RCG into the Works. |

## **AppendixAnnexure A: Summary of Hold Points, Witness Points, Milestones and Records**

General requirements for Hold Points, Witness Points, Milestones and Records are specified in Clause 5.2 of MRTS01 Introduction to Technical Specifications.

The Hold Points, Witness Points, Milestones and Records following is a summary of the Witness Points/Hold Points that apply to this specification and the Records that the Contractor must submit to the Principal Administrator to demonstrate compliance with this Technical Specification are summarised in Table A. There are no Witness Points or Milestones defined.

| <b>Clause</b> | <b>Hold point</b>                              | <b>Witness Point</b> |  | <b>Record</b>            |
|---------------|--|----------------------|--|--------------------------|
| 4.1           | 1. <u>Quality system conformance.</u>          |                      |  | <u>Quality Plan</u>      |
| 9.4           | 2. <u>Incorporation of RCG into the Works.</u> |                      |  | <u>Test Certificates</u> |

**Table A – Hold Points, Witness Points, Milestones and Records**

| <b>Clause</b> | <b>Hold Point</b>                             | <b>Witness Point</b> | <b>Milestone</b> | <b>Record</b>            |
|---------------|---|----------------------|------------------|--------------------------|
| <u>4.5</u>    | <u>1. Quality system conformance</u>          |                      |                  | <u>Quality Plan</u>      |
| <u>9.4</u>    | <u>2. Incorporation of RCG into the Works</u> |                      |                  | <u>Test Certificates</u> |

